

Legetolex 1432 pressure-sensitive constrained-layer damper


GENERAL DESCRIPTION

A market leader in performance, this product is a lightweight pressure-sensitive, constrained-layer damper that is versatile for many applications.

FEATURES

- Superior adhesive properties to many substates
- Aluminum foil constraining layer
- Effective vibration damping over a wide temperature range
- Available in various thicknesses and can have different gauge foil face sheets
- Provided in rectangular sheets or can be die-cut to specific geometry

PRODUCT CONSTRUCTION



APPLICATION

- Horizontal, vertical & inverted applications
- Temperature resistant and maintains adhesion through automotive bake cycles up to 200°C
- Applied in Stamping, Fab & Body Assembly operations:
 - Good adhesion to oily metal
 - Compatible with phosphating, E-coat & paint bake cycles
- Applied in Trim operations

PROPERTIES

| COLOR | Facing: Aluminum, Glass Cloth, Mylar Film Polymer: Black | |
|---|--|-----------|
| SHELF LIFE | At least 6 months when stored at 40°C or less | |
| TEMPERATURE RESISTANCE | Withstands a bake of 1 hour at 200°C with no deformation | |
| PEEL STRENGTH (90° Peel, 300 mm/min) | Oily Cold Rolled Steel | 38 N/25mm |
| | Oily Galvanized Steel | 36 N/25mm |
| | E-Coat (ED-11) | 60 N/25mm |
| | Can be bent around a 25 mm mandrel at -30°C with no | |
| | cracking or loss of adhesion | |
| DAMPING PROPERTIES | Composite Loss Factor ($\eta_c)$ between 0 and 60°C @ 200 Hz: | |
| (Per SAEJ1637, 0.8 mm test beam) | 0.1 – 0.32 | |