

Product:

# D5318


Product group:

**Double Coated Tapes** 

## General description

Nitto double-coated tape D5318 is a polyester carrier based tape with an agressive modified acrylic adhesive used for mounting of different types of plastics.

# Construction



Modified acrylic adhesive
Polyester carrier
Modified acrylic adhesive
PE-coated paper release liner

## Characteristics

Nitto D5318 is a double-coated tape with a high adhesion level on different substrates such as plastics, low surface energy substrates, foams and metals. The tape is suitable for rough surface bonding.

The white PET carrier provides dimensional stability resulting in reduced elongation and shrinkage. This tape provides the necessary opacity in order to reduce the amount of back printing operations.

## Application

Nitto D5318 is designed for mounting applications in sign and nameplate markets when white colour is needed.

### Features

- high adhesion on different plastics & rough surfaces
- high temperature resistance
- high holding power
- moisture stable liner
- easy processing
- RoHS compliant (2011/65/EC, 2015/863)

# **Technical Properties**

### General physical properties

	Typical value	Test Method	
Adhesive type	Colourless modified acrylic adhesive		
Tape thickness*	0.220 mm	EN 1942	
Release liner	Siliconised white PE coated paper (125 g/m²)		
Carrier type	White Polyester (0.050 mm)		
Adhesion to BA steel	2000 cN/20mm	EN 1939	
Release value	30 cN/50mm	Nitto Belgium Test Method	
Static shear	1 mm/3h	EN 1943	
Transport and storage conditions	Temperature 15 to 30 °C		
	Relative humidity 40 to 75% RH		

\* Tape thickness = Total thickness without liner

Details from the test methods are described on the customer product specification.

CAUTION: The above are typical values and should not be used in writing specifications.

#### Performance properties

Adhesion in cN/20mm			EN 1939	
PC	ABS	PP	Glass	
2100	2200	500	2600	
Weight Added Peel Off (WAPO) 2 h at 60°C, width 20mm, 100g				
PP 10 mm/2h	ABS 2	mm/2h	BA 2 mm/2h	
Dynamic Shear	500 N/40	cm² Te	sted after 15 min., 300mm/mi	n.
Saft test (Shear Adhesion Failure Temperature) 185 °C +0,5°C/min., 15x15mm, 200g				

### Warranty

The product is guaranteed to be free from defect in material and workmanship at the time of delivery and will be suitable for use for a period of 6 months thereafter, subject to the conditions set out herein.

## **Application guidelines**

- For optimum results, an even rub down pressure must be applied to the taped area to create the best possible adhesion between tape and the substrates.
- Remove the liner prior to usage.
- The tape should be applied to clean and dry surfaces.
- The best application conditions are obtained at a temperature between 15 °C and 40 °C.

If you require additional information on technical properties and application as well as product sampling or testing, please contact your local Nitto sales office.

#### General conditions of use and precautions:

The properties of the product might be adversely affected by various elements such as composition, condition and surface of and impurities in or on the substrate, temperature and humidity during storage and the surrounding environment at and after application and time of exterior use. When the product is used in combination with another material or process, the user shall assure the compatibility of the product in such combination and whether this combination results in the expected performance. The same principle applies in the event of product use in extreme conditions or circumstances, whether at or after the moment of application, including extended exposure to sunlight or extreme temperatures and pressure.

#### Packaging, transport and storage:

During transport and storage the product should always be protected against direct sunlight and extremes in temperature and humidity and contained in its original packaging. Once removed from its packaging, it should be promptly applied and remain shielded from direct sunlight and extreme temperature as well as protected against dust and other impurities.

#### Liability:

Except for its wilful misconduct, Nitto Belgium's liability shall be limited to a replacement, a reimbursement or an additional delivery of the product, and shall not exceed the purchase price of the products. In no event shall Nitto be liable in respect of any indirect or consequential damages, including loss of profits.

The above limitations of liability shall equally apply if Nitto Belgium has assisted in any manner with the selection, treatment or application of the product.

#### Product information:

This datasheet provides a general description of the product properties and application scope. Full technical details in connection with this product are presented in the customer product specification, which is available upon request.

Please be advised that the information reflected in this datasheet is subject to change and the product described herein may be modified or discontinued without notice.

Edition: January 2019 Code: DS/01.11/E4 D5318 ENG This datasheet replaces all previous versions

Nitto Belgium NV has obtained following certificates:

- ISO 9001 - ISO 14001

- IATF 16949
- Please check our website for applicable scope



For your local Nitto sales office, please visit our web site:

www.nitto.com

Copyright © 2019 NITTO BELGIUM NV. All rights reserved.