


Product: **R9410 - R9411**

Product group: **Repulpable Double-Coated Tapes**

## General description

Nitto repulpable double-coated tapes R9410 and R9411 consist of a non-woven tissue carrier, saturated with a water-soluble pressure sensitive adhesive. These tapes are recommended for automatic flying splices on almost all paper grades.

## Construction



## Characteristics

Nitto R9410 and R9411 have an extremely high tack resulting in excellent splicing properties, even at low temperatures and in humid environment.

The high temperature resistance keeps the splice intact during drying processes.

The tapes resist humidity for a limited period of time, although they are designed to be water-soluble. The release liner allows easy tearing of the excess paper in the splice area.

For storage, the tapes are hermetically sealed in plastic bags, to maintain constant moisture content.

Nitto R9410 and R9411 pass repulpability test by TAPPI Method UM-213-A.

## Application

Nitto R9410 and R9411 are suitable for splicing operations at high speed with automatic roll change in paper-and printing industries. The products can be used on off-coaters, sheeters, "flying pasters" and "zero-speed splicers".

## Features

- excellent splicing properties
- high temperature resistance
- easy tearing of the excess paper in the splice area
- repulpable according to TAPPI Method UM-213-A
- RoHS compliant (2011/65/EC, 2015/863)

## Technical Properties

### General physical properties

	Typical Value	Test Method
Adhesive type	R9410: colourless water-soluble acrylic R9411: green water-soluble acrylic	
Tape thickness*	0.080 mm	EN 1942
Release liner	White siliconised paper	
Release liner weight	95 g/m <sup>2</sup>	DIN 53104
Carrier type	Non-woven tissue	
Adhesion to test carton	600 cN/20mm	EN 1939
Release value	15 cN/50mm	Nitto Belgium Test Method
Transport and storage conditions	Temperature 15 °C to 30 °C Relative humidity 40 to 75% RH	

\* Tape thickness = Total thickness without liner  
Details from the test methods are described on the customer product specification.  
CAUTION: The above are typical values and should not be used in writing specifications.

### Performance properties

	Typical value	Test Method
Heat resistance	180 °C	3 min. , 200 g/cm <sup>2</sup>
Repulability	Good	Nitto Belgium Test Method (ISO 5263)
Dynamic Shear	170 N/4cm <sup>2</sup>	Tested after 15 min., 300mm/min.
Splicing Tack Level	High	Nitto Belgium Test Method
Oozing & Bleeding (1.5T/7days)	Major contamination	2x10 paper layers, RT/50% RH

## Warranty

The product is guaranteed to be free from defect in material and workmanship and will be suitable for use for the period as indicated on the packaging, subject to the conditions set out in the product specification.

## Application guidelines

- Keep the tape in its original individual packaging until use.
- For optimum results, an even rub down pressure must be applied to the taped area to create the best possible adhesion between tape and the web surface.
- Remove the liner prior to splicing.
- The tape should be applied to clean and dry surfaces.
- The best application conditions are obtained at a temperature between 15 °C and 40 °C.

If you require additional information on technical properties and application as well as product sampling or testing, please contact your local Nitto sales office.

### General conditions of use and precautions:

The properties of the product might be adversely affected by various elements such as composition, condition and surface of and impurities in or on the substrate, temperature and humidity during storage and the surrounding environment at and after application and time of exterior use.

When the product is used in combination with another material or process, the user shall assure the compatibility of the product in such combination and whether this combination results in the expected performance. The same principle applies in the event of product use in extreme conditions or circumstances, whether at or after the moment of application, including extended exposure to sunlight or extreme temperatures and pressure.

### Packaging, transport and storage:

During transport and storage the product should always be protected against direct sunlight and extremes in temperature and humidity and contained in its original packaging. Once removed from its packaging, it should be promptly applied and remain shielded from direct sunlight and extreme temperature as well as protected against dust and other impurities.

### Liability:

Except for its wilful misconduct, Nitto Belgium's liability shall be limited to a replacement, a reimbursement or an additional delivery of the product, and shall not exceed the purchase price of the products. In no event shall Nitto be liable in respect of any indirect or consequential damages, including loss of profits.

The above limitations of liability shall equally apply if Nitto Belgium has assisted in any manner with the selection, treatment or application of the product.

### Product information:

This datasheet provides a general description of the product properties and application scope. Full technical details in connection with this product are presented in the customer product specification, which is available upon request.

Please be advised that the information reflected in this datasheet is subject to change and the product described herein may be modified or discontinued without notice.

Edition: January 2019  
Code: DS/06.09/D1 R9410 R9411 ENG  
This datasheet replaces all previous versions

Nitto Belgium NV has obtained following certificates:

- ISO 9001
  - ISO 14001
  - IATF 16949
- Please check our website for applicable scope



For your local Nitto sales office, please visit our web site:  
[www.nitto.com](http://www.nitto.com)

Copyright © 2019 NITTO BELGIUM NV. All rights reserved.